



# CLIMAVER A2 deco

## CLIMAVER Self-supporting Ducts

### Description

High-density, ISOVER rigid glass wool panel; the external facing is covered with a decorative fibreglass fabric and an aluminium foil which acts as a vapour barrier, and the internal facing with a black reinforced glass neto fabric with high mechanical resistance.

### Applications

Given its superior acoustic and thermal insulation, **CLIMAVER A2 deco**, it is the ideal solution in order to meet the highest reaction to fire requirements when installing:

- Networks of self-supporting air-distribution ducts in thermal installations without false ceilings, within air-conditioning systems in buildings.

### Technical Properties

Symbol	Parameter	Icon	Units	Value	Standard
$\lambda_D$	Declared thermal conductivity as a function of temperature		W/m·K (°C)	0.032 (10) 0.033 (20) 0.036 (40) 0.038 (60)	EN 12667 EN 12939
	Reaction to fire		Euroclass	A2-s1, d0	EN 13501-1 EN 15715
MU	Mineral wool: water-vapour diffusion resistance, $\mu$		-	1	EN 12086
Z	Facing: water-vapour diffusion resistance		$m^2 \cdot h \cdot Pa / mg$	130	EN 12086
MV	The vapour diffusion-equivalent air layer thickness, $S_d$		m	100	EN 12086
DS	Dimensional stability, $\Delta\epsilon$		%	<1	EN 1604
	Airtightness		Class	D	UNE-EN 13403 EN 12237
	Pressure resistance		Pa	800	UNE-EN 13403

Working conditions: Air speed up to 18 m/s and circulating air temperature up to 90°C.

Thickness d, mm	Weighted acoustic absorption coefficient, $AW, \alpha_w$	Acoustic absorption class	Designation code
EN 823	EN ISO 354 EN ISO 11654	UNE EN ISO 11654	EN 14303
25	0.85 <sup>(1)</sup>	B	MW-EN 14303-T5-MV1

Acoustic trials with plenum: CTA 048/11/REV-5.

<sup>(1)</sup> Weighted acoustic absorption coefficient  $AW, \alpha_w$ , without plenum 0.55. CTA 140053/REV-7.

Frequency (Hz)	Frequency (Hz)					
	125	250	500	1000	2000	4000
Thickness d, mm	Practical acoustic absorption coefficient, $\alpha_p$ , EN ISO 354 / EN ISO 11654					
25	0.35	0.65	0.75	0.85	0.90	0.90
Section, S mm <sup>2</sup>	Acoustic attenuation, in a straight duct, $\Delta L$ (DB/m)*					
200x200	4.83	11.49	14.04	16.73	18.12	18.12
300x400	2.82	6.70	8.19	9.76	10.57	10.57
400x500	2.17	5.17	6.32	7.53	8.15	8.15
400x700	1.90	4.51	5.51	6.57	7.12	7.12
500x1000	1.45	3.45	4.21	5.02	5.44	5.44

\*Estimated by the formula:  $\Delta L = 1.05 \cdot \alpha_p^{1.4} \cdot \frac{P}{S}$ , (P = perimeter) for the sound power of a ventilator with a 20,000 m<sup>3</sup>/h flow, load loss 15 mm ca.

### Presentación



Thickness d (mm)	Length l (m)	Width b (m)	m <sup>2</sup> /package	m <sup>2</sup> /pallet	m <sup>2</sup> /truck load
25	3.00	1.19	24.99	149,94*	2.399

\*Possibility to supply half pallets  
Special colours available on request.

### Advantages

- Decorative aspect, rigid structure, vapour barrier and maximum protection in case of fire, without the need of additional exterior painting.
- Highest airtightness class.
- Optimal acoustic ambient quality and comfort class.
- Resistant to aggressive cleaning methods; UNE 100012.
- Duct union continuity. Exclusive male/female leaning shiplaps of the panels.
- No proliferation of mould and bacteria. Trials according to EN 13403
- Sustainable product. Recycled material > 50% 100% recyclable.
- Available in a wide range of colours.



### Certification



### Installation Guide

Consult the CLIMAVER Ducts Assembly Manual  
Additional information available at: [www.isover.es](http://www.isover.es)

[www.isover.es](http://www.isover.es)  
+34 901 33 22 11  
[isover.es@saint-gobain.com](mailto:isover.es@saint-gobain.com)  
[www.isover-aislamiento-tecnico.es](http://www.isover-aislamiento-tecnico.es)

@ISOVERes  
 ISOVERaislamiento  
 ISOVERaislamiento  
 isoveres

**ISOVER**  
SAINT-GOBAIN